



**COLORED STONE  
REPORT**

**ELECTRONIC  
COPY**



March 26, 2024

IGI Report Number	622483852
Species	NATURAL CORUNDUM
Variety	PINK SAPPHIRE
Shape and Cutting Style	PEAR MIXED CUT
Weight	0.73 CARAT
Measurements	6.87 x 4.73 x 2.74 mm
Color and Transparency	PURPLISH PINK, TRANSPARENT
Characteristics	NATURAL INCLUSION(S) PATTERN. NO INDICATIONS OF TREATMENT HAVE BEEN FOUND
Country of Origin	BASED ON CURRENT GEMOLOGICAL INFORMATION THE GEMSTONE DESCRIBED ABOVE WOULD BE CLASSIFIED AS BEING OF "MADAGASCAR" ORIGIN

March 26, 2024	
IGI Report Number	622483852
Species	NATURAL CORUNDUM
Variety	PINK SAPPHIRE
Shape and Cutting Style	PEAR MIXED CUT
Weight	0.73 CARAT
Measurements	6.87 x 4.73 x 2.74 mm
Color and Transparency	PURPLISH PINK, TRANSPARENT
Characteristics	NATURAL INCLUSION(S) PATTERN. NO INDICATIONS OF TREATMENT HAVE BEEN FOUND
Country of Origin	BASED ON CURRENT GEMOLOGICAL INFORMATION THE GEMSTONE DESCRIBED ABOVE WOULD BE CLASSIFIED AS BEING OF "MADAGASCAR" ORIGIN



**Species & Variety**

Gems may be classified in different species, according to their basic chemical composition and crystal structure; within a certain species, small differences in composition may result in different colors, or varieties.

The way that light interacts with the gem may create some astonishing optical phenomena, such as a star, a cat's eye effect or change of color, in different varieties

**Transparency**

As light passes through a gemstone, part of it, if not all, will be absorbed, and part will be transmitted. The more light that is absorbed the less transparent the stone will be.

**Characteristics**

Internal characteristics are the fingerprints of a gemstone. Not only do they provide essential information about the formation, but also the possible geological and geographical region where they originate from. Sometimes they also provide information about whether the gemstone has been treated.

**Refractive Index**

When light passes through air and enters a gemstone it slows down due to a difference in the medium. The ratio between the speed of light in air and in a particular medium is known the Refractive Index.

**Optic Character**

Determining how light travels through the crystal. Using a range of specialized instruments, we will be able to establish if the stone is isotropic or anisotropic, uniaxial or biaxial.

**Specific Gravity**

Specific gravity is the ratio of the density of the gemstone to the density of an equal volume of water.

All IGI Laboratories employ a wide range of state-of-the-art equipment, like FTIR and Raman spectrometers, all of which give a unique spectral graph for different gemstones. They can reveal the species of the gemstone, treatments and, at times, even the geographic origin.

**OPTICAL and PHYSICAL PROPERTIES**

Refractive Index	1.762 - 1.770
Birefringence	0.008
Optic Character	UNIAXIAL
Optic Sign	-
Specific Gravity	4.00

*Optical and physical properties are approximate values*



Photography is approximate



**IGI**



March 26, 2024  
622483852  
PEAR MIXED CUT  
0.73 CARAT  
NATURAL CORUNDUM  
PINK SAPPHIRE